



## **ONE COMPONENT PARQUET VARNISH**

| <b>Product Description</b>                   | It is a urethane based, one component, parquet varnish   |
|--|--|
| Product Code                                 | 785,30,830   |
| Properties                                   | Is an elastic varnish, high gloss, resistant to shock, scratch and outdoor conditions. Gives an excellent result on all kind of parquet, outdoor blinds, pergola, window joinery.  |
| Color  | Colorless  |
| Solid % (weight)                             | $56 \pm 1$   |
| Density<br>(@20°C, g/ml)                     | $0.97 \pm 0.05 \text{ g/ml}$   |
| Thinning Ratio                               | For spray application; with Hersen Thinner (908,01,800) $5 - 10\%$   |
|  | Volume   |
| Mixture Ratio                                | N/A  |
| Drying Time                                  | Dust Dry: $1 - 2$ hours.   |
|  | Touch Dry: 24 hours.   |
| Pot life                                     | -  |
| Application Viscosity<br>(@20 °C / DINCUP#4) | 30 – 35 s (brush)  |
|  | 16 – 17 s (spray)  |
| Coverage                                     | 120 – 150 g/ml for 50 – 60 micron dry film thickness   |
| Application                                  | to the raw surface Hersel Sanding Sealer is applied in two cross coats. Then left to dry for one day. One Component Parquet Varnish is applied in two cross coats by brush. For spray up applications the proper viscosity is achieved by diluting with Synthetic Thinner (908.01.800). For filled surfaces consumption of 200 - 250 g is suggested. |
| Remarks                                      | Store in dry and cool area and keep in closed packages. Keep packages closed when not<br>in use.<br>Keep away from sources of ignition- No smoking.<br>Use only in well -ventilated area.<br>Mix before use.   |

The above information is believed to be correct but does not purport to be all inclusive and shall be used only as a guide. The information in this document is based on the present state of our knowledge and it does not represent any guarantee of the properties of the product. Herkim Polimer Kimya San. ve Tic. A.S. and its Affiliates shall not be held liable for any damage resulting from handling or from contact with the above product.

AS-03.04/S-TDS-169 REV. NO/ TARIH: 00 / 08.11.2016

HERKİM POLİMER KİMYA SAN. ve TİC. A.Ş. A.O.S.B. 10004 Sokak No:4 P.K. 39 B.Çiğli/İZMİR • Tel : (0232) 376 72 41 (Pbx) • Fax : (0232) 376 72 40 İç Anadolu Bölge Müdürlüğü : Yağız Sk. No:14/B Siteler/ANKARA • Tel : (0312) 351 50 32 • Fax : (0312) 351 50 33 Akdeniz Bölge Müdürlüğü : Şafak Mah. 4259 Sk. No.14 ANTALYA • Tel : (0242) 221 21 15 • Fax : (0242) 221 24 77 www.herkim.com • e-mail: info@herkim.com

