

WOODLACK OUTDOOR VARNISH

Product Description	It is a two component varnish serie, which is suitable for outdoor applications due to its special resin structure.	
Product Code	Woodlack Matt Varnish (835,53,833) ~ 15-18 Gloss Woodlack Silk Matt Varnish (835,51,831) ~ 30-35 Gloss	
Properties	WOODLACK OUTDOOR VARNISH is a varnish for impregnated and with proper humidity outdoor woodwork. Its structure is elastic and contains UV filter. Its rapid drying property enables it to be suitable for bulk production. It can be applied both, water or solvent based colorants applied surfaces as well as raw surfaces without filler.	
Field of Application	is pergola, garden fence, blinds and window frames, all kinds of outdoor woodwork, garden furniture.	
Thinning Ratio	with Hersel Cellulosic Thinner (827.30.991) 60 – 65 %	
Mixture Ratio	Woodlack Outdoor Varnish Herodur Special Hardener	By Weight 5 part 1 part
Drying Time	Dust Dry: 15 min. Touch Dry: 60 min. Installation: after 24 hours	
Pot life	@20 °C 10 – 12 hours	
Application Viscosity (@20 °C / DINCUP#4)	As packed	
Coverage	with 1 kg mixed varnish, 12 -15 m ²	
Application	WOODLACK OUTDOOR VARNISH which is mixed in proper ratio, should be applied to the surface in two thin cross coats. In between the coats the surface should slightly be sanded. For the resistance to the outdoor conditions to be well, special care should be taken that the component and mixing ratio to be as indicated. For brush applications, after the mixing is complete, for dilution Duroflex Acrylic Thinner should be used.	
Remarks	Store in dry and cool area and keep in closed packages. Keep packages closed when not in use. Keep away from sources of ignition- No smoking. Use only in well -ventilated area. Mix before use.	



Ürün Teknik Bülteninde yer alan bilgiler laboratuvar koşullarında elde edilmiştir. Firmamız hiçbir suretle bu bilgilere gösterilen itibardan ve bunların kullanılmasından doğabilecek doğrudan, dolaylı, özel ve sonuç niteliğindeki kayıp ve zararlardan dolayı sorumlu tutulamaz. Malzeme güvenlik bilgi formları istek üzerine verilir.

AS-03.04/S-TDS-63 REV. NO/ TARİH: 00 / 03.03.2016