

DEKOSEN UVF TOPCOAT PAINT

Product Description	Synthetic resin based, decorative and protective topcoat with high resistance to atmospheric conditions and especially UV rays.
Product Code	714,serie (high gloss, silk matt, matt)
Color	Any desired color
Properties	It is used for decoration and protection on all wooden surfaces both inside and outside. On external conditions, it is resistant to sun rays and moisture, and the winding resistance is high.
Solid Content	67 ± 2%
Density	1,20 ± 0,05 g/ml
Thinning Ratio	For brush application; With Dekosen Synthetic Thinner (908,01,800) %20-25 For spray application; With Dekosen Synthetic Thinner (908,01,800) %30-35 Weight
Mixture Ratio	-
Dry Time	Dust dry 30 – 40 min Touch dry 2 – 3 hours
Pot life @20 °C	-
Application Viscosity @20 °C, DINCUP #4	40 - 50 s (roller application) 16 - 18 s (spray application)
Coverage	120 – 150 g/m ² (for 50 – 60 micron dry film thickness)
Application	After 1 - 2 hours after applying Dekosen UVF primer, thinned Dekosen UVF Topcoat is applied in thin layers on the surface with a paint brush or spray gun. Allowing a sufficient time interval between the layers in the finish coat application and sanding the surface before the final blanket will provide a smoother surface finish.
Remarks	Store in dry and cool area and keep in closed packages. Keep packages closed when not in use. Keep away from sources of ignition- No smoking. Use only in well -ventilated area. Mix before use.

The above information is believed to be correct but does not purport to be all inclusive and shall be used only as a guide. The information in this document is based on the present state of our knowledge and it does not represent any guarantee of the properties of the product. Herkim Polimer Kimya San. ve Tic. A.Ş. and its Affiliates shall not be held liable for any damage resulting from handling or from contact with the above product.

AS-03.04/S-TDS-49 REV. NO/ DATE: 00 / 03.03.2016

