

SATINFLEX SCRATCH RESISTANT VARNISH

Product Description	It is a polyurethane based, two component,matt or silk matt having parquette varnish, which has scratch resistant property.		
Product Code	945,31,serie (silk matt; 40 – 45 Gloss) 945,33, serie (matt; 20 – 25 Gloss)		
Properties	it can be used on parquet, stairs and panels.		
Color	Colorless		
Solid % (weight)	25% ± 1		
Density (@20°C, g/ml)	1,00 ± 0,05 g/ml		
Thinning Ratio	Roller application	40 % with Hersel Polyurethane Thinner	
	Spray Up applications	55 % with Hersel Cellulosic Thinner	
		By weight	
Mixture Ratio	Satinflex Scratch Resistant Varnish	3	
	Herodur Universal Hardener (827.00.802)		1
	(to obtain the desired surface quality, above given ratio should strictly be obeyed)		
Drying Time	Dust Dry: 15 min. Touch Dry: 30 min.		
Pot life	@20 °C	10 – 12 hours	
Application Viscosity (@20 °C / DINCUP#4)	15 – 16 s		
Coverage	7 – 8 m² / kg		
Application	Before the application, the surface should be dry and clean, and the cracks on the surface should be filled. Then sanding sealer, cellulosic or polyurethane, is applied. Sanding should be done after the surface is dry. Then SATINFLEX SCRATCH RESISTANT VARNISH, mixed with the above given ratios, is applied either by brush or paint gun in 1-2 cross coats and left to dry. The result will be more satisfactory if a time interval of 3-4 hours left in between the cross coats. After application the brush or other paint tool should be cleaned with Hersel Cellulosic Thinner.		
Remarks	Store in dry and cool area and keep in closed packages. Keep packages closed when not in use. Keep away from sources of ignition- No smoking. Use only in well -ventilated area. Mix before use.		

The above information is believed to be correct but does not purport to be all inclusive and shall be used only as a guide. The information in this document is based on the present state of our knowledge and it does not represent any guarantee of the properties of the product. Herkim Polimer Kimya San. ve Tic. A.Ş. and its Affiliates shall not be held liable for any damage resulting from handling or from contact with the above product.

AS-03.04/S-TDS-90 REV. NO/ TARİH: 00 / 03.06.2016

HERKİM POLİMER KİMYA SAN. ve TİC. A.Ş.

A.O.S.B. 10004 Sokak No:4 P.K. 39 B.Çiğli/İZMİR • Tel : (0232) 376 72 41 (Pbx) • Fax : (0232) 376 72 40

İç Anadolu Bölge Müdürlüğü : Yağız Sk. No:14/B Siteler/ANKARA • Tel : (0312) 351 50 32 • Fax : (0312) 351 50 33

Akdeniz Bölge Müdürlüğü : Şafak Mah. 4259 Sk. No.14 ANTALYA • Tel : (0242) 221 21 15 • Fax : (0242) 221 24 77

www.herkim.com • e-mail: info@herkim.com

